



Providing Solutions in Pressure Sensitive Films

Product Construction Sheet

FLEXmount® TT 400 A-326 60 LA PFW

GENERAL DESCRIPTION:

This is a 4.0 mil (102 micron) permanent pressure sensitive acrylic adhesive supported with a two side poly coated semi-bleached kraft differential release liner.

NOTE:

For all testing, transfer tape was laminated to 2.0 mil (51 micron) clear polyester (PM 200 CLEAR) film. Use with plasticized vinyl surface is not recommended.

PRODUCT DATA	VALUE	TEST METHOD
PHYSICAL PROPERTIES		
Thickness mil (micron)	Adhesive: 3.9-4.1 (99-104) +/- 0.1 (3) Liner: 4.3 (109) +/- 10 %	ASTM D 3652

ADHESION PROPERTIES**

Adhesion from	Average oz/in (N/m)	
Stainless Steel	110 (1210)	ASTM D 903 (Modified for 72 hr dwell time)
Acrylic	141 (1551)	
Glass	128 (1408)	
Polypropylene***	34 (374)	
Expected Shear (hours)	50	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (gm)	1140	ASTM D 2979

** For guidance only, not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs. *** Zippy adhesion.

EXPECTED EXTERIOR LIFE	Depends on substrates, adhesive is suitable for outdoor use
SERVICE TEMPERATURE	-40°F to 302°F (-40°C to 150°C)
MINIMUM APPLICATION TEMPERATURE	50°F (10°C)
STORAGE STABILITY	Two years stored at 70°F (21°C) and 50% RH

* FLEXmount is a registered trademark of FLEXcon Company, Inc.

11/30/2006

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.