



Product Construction Sheet

ThermiFilm HT PI2W50GV2



General Description

A high temperature white polyimide film , topcoat for conventional printing, thermal transfer printing with resin and combo ribbons, as well as UV inkjet, coated with a permanent high performance acrylic adhesive backed with a glassine liner.

Product Data		Value		Test Method
Physical Properties				
Thickness (micron)	Film and coating	66	+/-15 %	ASTM D 3652
	Adhesive	35-38	+/- 3	
	Liner	69	+/- 10 %	
Dimensional Stability (%)	Machine Direction	No shrinkage observed		On AL panel at 70°C for 24 hr.

Adhesive Properties**

Adhesion from (N/25mm)	Average		
Stainless Steel	638		FTM 1 (72 hr dwell time)
Glass	627		
Acrylic	605		
PP	33		
Expected Shear (Hours)	25		FTM 8
Tack (gm/sq cm)	1100		ASTM D 2979

UL RECOGNITION:

This product is UL recognized for indoor/outdoor use with occasional exposure to lubricating oil and water. For further information, please reference FLEXcon's UL file No MH16635 (N) or contact your FLEXcon Representative.

NOTE: This is an experimental product, customer must qualify it for the intended end-use application. Customer feedback is required to commercialise this product. Properties may change or product withdrawn from the market (discontinued)

*** For guidance only

This data is based on limited test results on adhesive coat weight of: This data is based on limited test results on adhesive coat weight of: 22 micron. Due to the custom nature of this product, not to be used for setting specifications.

Expected Exterior Life	2 years
Service Temperature Range	-40°C to 180°C (Intermittent 398°C)
Minimum Application Temperature	10°C
Storage Stability	2 years stored at 21°C and 50% RH

* ThermiFilm is a trademark of Flexcon Company Inc

10/02/2025

S 1479

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon. Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. **FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.**