



# Flexcon® OptiFlex® ConformMax™ PE30453 - 3.0 Mil White PE, Permanent Adhesive TracRite 120

Primary and Secondary Labeling

FLX011312

## Benefits

## Features

- 3 mil white polyethylene film
- Polyester release liner for excellent on-press performance for tight-registration graphics
- Liner provides good diecutting base and allows for high-speed dispensing

## Additional Details

## Technical Data

### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.7	
Film	3.0 +/- 10 %	76
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	Liner: 1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	74	814
Acrylic	63	693
Glass	73	803
Polypropylene	18	198

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	5	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	570	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.