



Benefits

- Excellent stayflat release liner properties for printing and converting

Features

- 3.5 mil semi-flexible white vinyl film resists on-liner and applied shrinkage
- Printable via UV Offset, Solvent and UV Screen, Solvent and UV Inkjet, and Latex
- Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including low surface energy plastics, paper, wood, glass and metal
- Backed with a layflat 90 lb. moisture stable polycoated release liner ideal for sheet-form converting

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.25	
Film	3.5 +/- 10%	89
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	73	803
Glass	70	770
Polypropylene	32	352
Styrene	70	770
Polyethylene	27	297

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	10	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	370	ASTM D 2979
Expected Exterior Life	Two Years	
Additional Information	Chemical Resistance, Water Good, Gasoline Fair, Basic Cleaners Good, Toluene Poor, ASTM D 896 (Modified for number of cycles and cycle time)	
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.