

Flexcon® CompuCal® Excel™ 10442

1.0 Mil Matte Topcoated Clear Polyester Overlaminate, Permanent Adhesive, Poly Liner FLX012395

Benefits

- · Overlaminating polyester resists temperature extremes, abrasion and chemical exposure for maximum label protection
- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- CSA accepted under CSA File No. 99214

Features

- 1.0 mil matte topcoated clear overlaminating polyester provides excellent clarity and label protection
- This thin gauge film can also be used as a printable base film alternative to the standard 2.0 mil product
- Matte topcoated film designed for cross-technology printability via impact, laser, electron beam, wax, resin and wax/resin thermal transfer (we recommend
 evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- Unique matte topcoat allows for greater than four times as many die revolutions before retooling compared with competing label materials
- Topcoat provides excellent resistance to chemicals, moisture, smudging and scratching
- Permanent pressure-sensitive acrylic adhesive bonds well to base film substrates, as well as low-surface energy plastics, metal and powder-coated paint
- Backed with an ultra smooth clear polyester release liner

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns	
Total Product	3.2		
Film	1.1 +/- 10%	28	
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3	
Liner	1.0 +/- 5%	25	

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® CompuCal® Excel™ 10442

1.0 Mil Matte Topcoated Clear Polyester Overlaminate, Permanent Adhesive, Poly Liner FLX012395

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	48	528
Acrylic	61	671
Glass	43	473
Polypropylene	27	297

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	25	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	830	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.