



## Benefits

- For Tamper-Evident Labeling including: Consumer Electronics or anywhere tamper evidence may be required.

## Features

- 2.0 mil clear diacetate film for destructible applications
- Printable surface is compatible with most standard flexographic inks
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Backed with an ultra-smooth clear polyester release liner
- Release liner provides a good diecutting base and allows for high-speed dispensing

## Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.14	
Film	2.0 +/- 10 %	51
Adhesive	0.7-0.8 +/- 0.1	18-20 +/- 3
Liner	1.4 +/- 10 %	36

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Glass	59	649
Polypropylene	2	22
Acrylic	67	737

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	30	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	700	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.