

Benefits

• Adhesive bonds well to printed base surface

Features

- 8.0 mil velvet polypropylene
- UV absorbing/resistant high-performance permanent acrylic pressure-sensitive adhesive enhances and provides added protection to digitally-printed graphics
- Backed with an ultra-smooth clear polyester release liner
- Release liner provides a good diecutting base and allows for high-speed dispensing

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.04	
Film	8.5 +/- 15 %	216
Adhesive	1.4-1.5 +/- 0.1	36-38 +/-3
Liner	1.4 +/- 10 %	36

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	39	429
Acrylic	79	869
Glass	60	660
Polypropylene	4	44

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method		
Expected Shear (hours)	75	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)		
Tack (g)	360	ASTM D 2979		
Expected Exterior Life	Two years (Based on 1000 hou	Two years (Based on 1000 hours Xenon-arc testing)		
Additional Information				
Service Temperature	-40°F to 212°F (-40°C to 100°C	-40°F to 212°F (-40°C to 100°C)		
Minimum Application Temperature	50°F (10°C)	50°F (10°C)		
Storage Stability	Two years stored at 70°F (21°C humidity) and 50% relative		

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.