

## Flexcon® OptiFlex® Polypropylene 230 H White TC-332™ A-32 TracRite™ 150

Primary and Secondary Labeling White Polypropylene FLX000146

### **Benefits**

- Excellent surface smoothness allows for optimum ink laydown
- Film conformability for rigid containers provides maximum label and graphic coverage

### **Features**

- 2.3 mil white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping
- Permanent pressure-sensitive acrylic adhesive bonds well to glass, low- and high-surface energy plastics without lifting, tunneling or flagging
- Adhesive offers excellent tack, clarity and wet-out characteristics
- Backed with Flexcon® TracRite™ 150 polyester release liner for excellent on-press performance for tight registration graphics
- Release liner provides a good diecutting base and allows for high-speed dispensing

### **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4.71	
Film	2.3 +/- 10%	58
Adhesive	0.55-0.6 +/- 0.1 (3)	14-17
Liner	1.4 +/- 10%	36

Test Method: ASTM D 3652 (Modified for use with non-tape products)



## Flexcon® OptiFlex® Polypropylene 230 H White TC-332™ A-32 TracRite™ 150

Primary and Secondary Labeling White Polypropylene FLX000146

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	38	418
Glass	43	473
Polycarbonate	50	550
Styrene	44	484

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	470	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.