# Flexcon® OptiFlex® PP 230 H White TC-458 V-81 TracRrite™ 120

Primary and Secondary Labeling White Polypropylene Rigid Container Labels Semi-Squeeze Container Labels

FLX000159

## Benefits

- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing

## Features

- 2.3 mil hard white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film conformability for rigid containers provides maximum label and graphic coverage
- Excellent surface smoothness allows for optimum ink laydown
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping

## Additional Details

## Technical Data

**Physical Properties**

| Thickness (Mils [microns]) | Mils | Microns |
|---|---|---|
| Total Product | 4.47 | |
| Film | 2.3 +/- 10 % | 58 |
| Adhesive | 0.5-0.6 +/- 0.1 | 13-15 +/- 3 |
| Liner | 1.2 +/- 10 % | 30 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)

**Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|---|---|---|
| Stainless Steel | 53 | 583 |
| Acrylic | 46 | 506 |
| Glass | 47 | 517 |
| Polypropylene | 10 | 110 |

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

| Additional Properties | Value | Test Method |
|---|---|---|
| Expected Shear (hours) | 15 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 710 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -40°F to 212°F (-40°C to 100°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.

© 2026 Flexcon, Inc. All rights reserved.