

## **Benefits**

- Flexcon® TracRite<sup>™</sup> 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing
- Film clarity is ideal for achieving the no-label-look on glass

#### **Features**

- 2.0 mil clear polypropylene (BOPP) film offers excellent resistance to shrinkage, high temperature pasteurization, moisture, humidity and product contents
- Excellent surface smoothness allows for optimum ink laydown
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping

# **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4.15	
Film	2.0 +/- 10 %	51
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	48	528
Glass	47	517
Polypropylene	13	143
Acrylic	42	462

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	15	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	740	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.