

# Flexcon® OptiFlex® PP 200 H CLEAR TC-332™ V-32 TRACrite™ 120

 $\overline{2.0}$  mil clear polypropylene (BOPP) film for primary and secondary labeling FLX000167

## **Benefits**

- Ideal for neck label applications
- High-performance permanent acrylic adhesive provides a good bond to low- and high-surface energy plastics, and glass for reliable performance in extreme cold temperatures
- polyester release liner for excellent on-press performance for tight-registration graphics
- polyester release liner contains up to 60% Post Industrial Recycled content, provides good diecutting base and allows for high-speed dispensing

## **Features**

- 2.0 mil clear polypropylene (BOPP) film offers excellent resistance to shrinkage, high temperature pasteurization, moisture, humidity and product contents
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Film clarity is ideal for achieving the no-label-look on glass
- Excellent surface smoothness allows for optimum ink laydown
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping

## **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4.35	
Film	2.0 +/- 10%	51
Adhesive	0.7-0.8 +/- 0.1 (3)	18-20
Liner	1.2 +/- 5%	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® OptiFlex® PP 200 H CLEAR TC-332™ V-32 TRACrite™ 120

2.0 mil clear polypropylene (BOPP) film for primary and secondary labeling FLX000167

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Glass	37	407
Polyester	43	473
Polyethylene Corona Treated	27	297
Polypropylene	6	66
PVC	58	638

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	280	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.