



## Benefits

- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting

## Features

- 3.5 mil flexible white vinyl provides durability for ease of installation and removal
- Printable via UV Offset, Solvent and UV Screen, Solvent and UV Inkjet, and Latex
- Suitable for mounting on the outside and inside of windows
- Intended for use on glass only
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass interior and exterior surfaces over a wide range of temperatures while removing cleanly

## Additional Details

Please refer to [Flexcon's Window Graphics Installation Guide](#) for more information.

## Technical Data

### Physical Properties

| Thickness (Mils [microns]) | Mils                | Microns |
|----------------------------|---------------------|---------|
| Film                       | 3.5 +/- 10%         | 89      |
| Adhesive                   | 0.8-0.9 +/- 0.1 (3) | 20-23   |
| Liner                      | 6.9 +/- 10%         | 175     |

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Non-tinted Glass   | 13            | 143   |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties           | Value                                      | Test Method |
|---------------------------------|--|-------------|
| Expected Shear                  |  |             |
| Tack                            | 70   | ASTM D 2979 |
| Expected Exterior Life          | Two years                                  |             |
| Additional Information          |  |             |
| Service Temperature             | -20°F to 176°F (-29°C to 80°C)             |             |
| Minimum Application Temperature | 50°F (10°C)                                |             |
| Storage Stability               | One years stored at 70°F (21°C) and 50% RH |             |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.