



Benefits

Please refer to [Flexcon's Window Graphics Installation Guide](#) for more information.

Features

- 4.0 mil hard clear vinyl provides durability for ease of installation and removal
- Primed for excellent ink adhesion and printability via UV and conventional offset; solvent and UV screen; solvent and UV inkjet; and UV, solvent and water flexo
- Suitable for mounting on the outside and inside of windows
- Intended for use on glass only
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass interior and exterior surfaces over a wide range of temperatures while removing cleanly
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting

Additional Details

Caution: When using the wet application method, this product may haze. Under normal temperature and humidity conditions, the hazing usually clears within 48 hours.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	12.05	
Film	4.0 +/- 10%	102
Adhesive	0.8-0.9 +/- 0.1 (3)	20-23
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Glass	7	77

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	100	ASTM D 2979
Expected Exterior Life	One year	
Additional Information		
Service Temperature	-20°F to 176°F (-29°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.