Flexcon® FlexMark® OV6601 6.5 Mil Clear Velvet Vinyl Overlaminate

6.5 Mil Rigid Clear Velvet Overlaminate for indoor floor advertising.

FLX019124

Benefits

- Velvet finish enhances graphic images, prevents glare

Features

- 6.2 mil velvet embossed rigid clear overlaminating vinyl film protects the printed graphic
- Permanent overlaminating pressure-sensitive acrylic adhesive bonds well to base film surface
- Backed with a 71 lb. smooth bleached white polycoated kraft release liner ideal for roll-form converting
- Smooth release liner provides improved adhesive clarity for vibrant graphics

Additional Details

FlexMark® OV6601 with FlexMark® Floor Art™ 4652, FlexMark® Floor Art™ 6610, or FlexMark® Floor Art™ 6640has been investigated by Underwriters Laboratories, Inc., and when used as a system, is in accordance with UL 410, the Standard for Floor Surfaces, for Floor-Graphic Materials (FGM).

Please refer to Flexcon's Warranty & Limited Remedy Policy for Graphic Advertising for Floors and Indoor Carpets, and Application and Removal Instructions.Nothing contained herein shall expand the Floors and Indoor Carpets Limited Warranty or otherwise be construed as a warranty or guarantee.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	12.45	
Film	6.2 +/- 15%	158
Adhesive	1.6-1.7 +/- 0.1	41 - 43
Liner	4.3 +/- 10%	109

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	162	1782
Glass	109	1199
Stainless Steel	113	1243

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	100	ASTM D 3654 1 hr. dwell
Tack (g)	660	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity Product	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.

© 2026 Flexcon, Inc. All rights reserved.