



Benefits

- Backed with Flexcon® TracRite™ 150 polyester release liner for excellent on-press performance for tight registration graphics
- Release liner provides a good diecutting base and allows for high-speed dispensing

Features

- 2.0 mil clear polypropylene (BOPP) offers excellent resistance to shrinkage, high temperatures, moisture, humidity and product contents
- Polypropylene is a more economical alternative to polyester
- Film clarity is ideal for achieving the no-label-look on clear vials and syringes
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping (We recommend evaluating the intended ink system for compatibility with the product under the application conditions)
- Permanent pressure-sensitive acrylic adhesive bonds well to glass and polypropylene
- Adhesive offers excellent tack, clarity and wet out characteristics

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10 %	51
Adhesive	0.6-0.7 +/- 0.1	15-18 +/- 3
Liner	1.4 +/- 10 %	36

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	36	396
Glass	39	429
Polypropylene	6	66
Acrylic	44	484

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	100+	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack	480	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.