FlexMark® DA 200 Clear V-88 Special 50K/Q-8

Clear diacetate film for destructible applications

FLX000214

Benefits

- Aggressive permanent rubber based adhesive offers excellent adhesion to a wide variety of surfaces

Features

- 2.0 mil clear diacetate film for destructible applications
- Backed with a 50 lb. semi-bleached kraft release liner that is Quilon®* coated

Additional Details

*Quilon® is a registered trademark of Zaclon, LLC.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.25	
Film	2.0 +/- 10 %	51
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	3.2 +/- 10 %	81

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel		Film rips during adhesion test
Acrylic		Film rips during adhesion test
Glass		Film rips during adhesion test
Polypropylene		Film rips during adhesion test

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	100	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	1340	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 200°F (-40°C to 93°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.

© 2026 Flexcon, Inc. All rights reserved.