



FlexMount® DFM 200 White V-344 100 POLY H-9 V-606 200 POLY SC-6 (1.9-2.1)

FLX022740

Benefits

- Permanent acrylic adhesive offers medium tack, high shear and excellent adhesion to a variety of metal and plastic surfaces, including polypropylene, polyethylene, PORON® and Kushon® cellular rubber products

Features

- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, moderately rough surfaces. polycarbonate and fiberglass
- High-peel permanent acrylic adhesive resists cold flow and ooze
- Performance, aggressive, permanent pressure-sensitive adhesive bonds well to a variety of surfaces
- Ultra-smooth polyester release liner provides ultimate smoothness and flow-out of adhesive on the overlaminating film
- Adhesive offers high initial tack, high shear, and high ultimate bond to a wide variety of rough textured surfaces, including low-surface energy plastics and painted metal

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.97	
Film	2.0 +/- 10	51
Adhesive	V-606: 1.9-2.1 +/- 0.1	V606: 48-53 +/- 3
Adhesive 2	V344: 1.0-1.1 +/- 0.1	V344: 25-28 +/- 3
Liner	200 POLY SC-6 Liner: 2.0 +/- 1	200 POLY SC-6 Liner: 51
Liner 2	100 POLY H-9 Liner: 1.0 +/- 1	100 POLY H-9 Liner: 25

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	V-344: 55 V-606: 104	V-344: 605 V-606: 1144
Acrylic	V-344: 77 V-606: 112	V-344: 847 V-606: 1232
Glass	V-344: 68 V-606: 118	V-344: 748 V-606: 1298
Polypropylene	V-344: 15 V-606: 22	V-344: 165 V-606: 242

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	V-344: 30 V-606: 100	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	V-344: 1030 V-606: 1520	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.