



## BusArt™ OV5055 2 Mil Clear Cast Laminating Vinyl

Transit: Bus & Train Wraps - Window Perf Optically Clear Overlamine  
FLX024229

### Benefits

- 7 years expected exterior life
- Approved by OUTFRONT Media and Vector Media for full bus and train wraps, ultra kings, ultra super kings, fullbacks and halfbacks
- Overlamine is part of the Painted-On-Look Cast System, Flexcon® FlexMark® BilBrd™ CWRTS and BusArt™ OV5055 - for rough textured walls. Graphics applied with heat gun and foam roller

### Features

- 2.0 mil clear cast vinyl overlamine with optically clear adhesive

### Additional Details

- This product is part of Flexcon's Bus and Train Wrap Advertising System. It can be used with Flexcon® SeeThru-Sign® STSWBF2 (Base Film). For installation instructions, visit: [Flexcon's Transit Technical Guide and Installation Instructions](#).
- BusArt™ OV5055 meets flammability requirements ASTM E 162 – Standard Test Method for Surface Flammability of Materials Using a Radiant Heat Energy Source and ASTM E 662 – Standard Test Method for Specific Optical Density of Smoke Generated by Solid Materials
- This product is part of the Painted-On-Look Cast System, FlexMark® BilBrd™ CWRTSbase film and BusArt™ OV5055 overlamine for wall graphics. For installation instructions, visit: [Flexcon's Technical Guide and Application Instructions](#).

\*Optical clarity has many interpretations. Its use in the description of BusArt™ OV5055 is market/application specific to overlaminates used for perforated window films in bus wraps where there are no specifications for haze and/or light transmission required.

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	3.97	
Film	2.0 +/- 10 %	51
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	1.0 +/- 5%	25

Test Method: ASTM D 3652 (Modified for use with non-tape product)



BusArt™ OV5055 2 Mil Clear Cast Laminating Vinyl

Transit: Bus & Train Wraps - Window Perf Optically Clear Overlamine  
FLX024229

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	43	473
Acrylic	65	715
Glass	53	583
Polypropylene	17	187

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	20+ (Film rips)	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	270	ASTM D 2979
Expected Exterior Life	Seven years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.