

Flexcon® FlexMark® V 400 F Black TC-848 V-465 Special 50K-8

Bumper Stickers Permanent - Roll-Form FLX000026

Benefits

• Ideal for roll converting and manual dispensing

Features

- 3.5 mil flexible vinyl film for easy application
- Topcoat optimizes printability with most standard flexographic inks. (Please test for ink adhesion with your specific ink chemistry.)
- · Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including paper, wood, glass and metal
- 50 lb. bleached kraft release liner offers good diecutability
- Product suitable for thermal diecutting

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------------|---------|
| Total Product | 7.7 | |
| Film | 3.5 +/- 10% | 89 |
| Adhesive | 0.75-0.85 +/- 0.1 (3) | 19-22 |
| Liner | 3.1 +/- 10% | 79 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® FlexMark® V 400 F Black TC-848 V-465 Special 50K-8

Bumper Stickers Permanent - Roll-Form FLX000026

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Glass | 45 | 495 |
| Painted Metal | 43 | 473 |
| Painted Wallboard | 15 | 165 |
| Painted Wood | 11 | 121 |
| Paper | 36 | 396 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|-------------|
| Expected Shear | | |
| Tack | 230 | ASTM D 2979 |
| Expected Exterior Life | Two years (vertical exposure, mid continental North America) | |
| Additional Information | | |
| Service Temperature | -20°F to 176°F (-29°C to 80°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% RH | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.