Flexcon® CompuCal® Excel™ 22449

Durable Goods and Equipment Labeling Matte Topcoated Silver Polyester - Thermal Transfer Printable

FLX000287

Benefits

- UL recognized under UL 969 - UL File No. PGJI2.MH16635 Printing Materials - Component
- CSA accepted under CSA File No. 99214
- View CompuCal® Excel™ 22449 Yellow Card

Features

- 2.0 mil matte topcoated silver polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Matte topcoated film designed for cross-technology printability via narrow-format UV inkjet, impact, laser, electron beam, wax, resin and wax/resin thermal transfer (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions
- Unique matte topcoat allows for greater than four times as many die revolutions before retooling compared with competing label materials
- Topcoat provides excellent resistance to chemicals, moisture, smudging and scratching
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- White, layflat two-side polycoated release liner with a highly engineered backside, friction-coated layer which enables excellent tracking on press and reliable feeding through tabletop and big box laser printers
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.05	
Film	2.1 +/- 10 %	53
Adhesive	0.9-1.0 +/- 0.1	23-25 +/- 3
Liner	7.4 +/- 10 %	188

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Glass	68	748
Polypropylene	15	165
Acrylic	77	847

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	30	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	1030	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.

© 2026 Flexcon, Inc. All rights reserved.