Flexcon® WallDeco™ 6730

6.0 Mil Vinyl, High-Tack Removable Adhesive, Sheet Liner FLX028884

Benefits

- REACH SVHC compliant
- Meets flammability requirements ASTM E 84 Class I or A Rated

Features

- . 6.0 mil white vinyl with a smooth surface for graphic reproduction, and the handle of the film provides ease in installation
- Printable via UV and solvent screen, UV and solvent inkjet, UV offset, and latex
- High-tack removable pressure-sensitive adhesive bonds well to smooth painted (non-vinyl) wallboards
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting

Additional Details

Please click hereto view Flexcon's Wall Graphics Technical Guide and Application Instructions.

For Inkjet Printing:

- Typical max. ink limit = 250%
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

None of the REACH SVHC on the current candidate lists are knowingly used or intentionally added to the raw materials used to produce this product

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	13.35	
Film	6.0 +/- 10%	152
Adhesive	6.9 +/- 10%	175
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® WallDeco™ 6730

6.0 Mil Vinyl, High-Tack Removable Adhesive, Sheet Liner FLX028884

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Smooth Painted (non vinyl) Wal	1	11

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method	
Expected Shear (hours)			
Tack (g)	220	ASTM D 2979	
Expected Exterior Life	Indoor use only		
Additional Information	Flammability ASTM E 84 Class I or A F Removability Up to 6 months from smo (non-vinyl) wallboards	Rated. ooth painted	
Service Temperature	-20°F to 176°F (-29°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	Two years stored at 70°F (21°C) and 5 humidity	0% relative	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.