



Benefits

Features

- 3.6 mil flexible white polyolefin (non-vinyl "greener") phthalate-free film that produced with less solvent with a smooth surface for graphic reproduction
- Printable via UV and solvent screen, and UV inkjet reducing VOC emissions
- Phthalate free and produced with less solvent as compared to solvent adhesive systems
- Complies with CONEG and CPSIA
- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass interior and exterior surfaces over a wide range of temperatures while removing cleanly
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting
- Overlaminating will extend the life of the graphic - contact your Flexcon Technical Service representative for more information

Additional Details

Definitions: CONEG = Northeastern Governors; CPSIA = Consumer Products Safety Improvement Act; and VOCs = Volatile Organic Compounds).

Please refer to [Flexcon's Window Graphics Installation Guide](#) for more information.

For Inkjet Printing:

- Typical max. ink limit = 250%
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.25	
Film	3.6 +/- 10%	91
Adhesive	0.8-0.9 +/- 0.1 (3)	20-23
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Non-tinted Glass	4	44

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	200	ASTM D 2979
Expected Exterior Life	Up to one year	
Additional Information		
Service Temperature	-20°F to 176°F (-29°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.