

## Flexcon® FlexMount® TT 200 V-778 200 POLY LA

2 Mil Permanant Adhesive Transfer Tape on a Single 2 Mil Polyester Liner FLX029363

## **Benefits**

- To form a permanent bond, surfaces need only to be cleaned with an IPA/water wash, eliminating the need for flame treatment or pre-application primers
- Extruded polyester release liner offers smoother surface profile for improved adhesive wet-out compared to paper liners
- Liner can be considered recyclable in some geographic areas

## **Features**

- 2.0 mil transfer adhesive
- High-performance adhesive that will permanently adhere to a variety of surfaces such as low-surface energy plastics, painted metal, powder coated paint, polycarbonate and fiberglass
- Adheres to smooth and textured TPO's and other low-energy surfaces.
- 2 mil polyester liner is strong enough to conform to tight angles and works well for automated assembly and robotic application
- Liner is ideal for auto processing and diecutting, industrial processing and clean room environment

## **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4.88	
Adhesive	1.9-2.1 +/- 0.1 (3)	48-53
Liner	2.0 +/- 5%	51

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® FlexMount® TT 200 V-778 200 POLY LA

2 Mil Permanant Adhesive Transfer Tape on a Single 2 Mil Polyester Liner FLX029363

#### **Adhesion Properties**

Ultimate Peel from Average Oz/In	(N/m)	
----------------------------------	-------	--

### Test Method:

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	1020	ASTM D 2979
Expected Exterior Life	Two years (one year direct sunlight)	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.