



Flexcon® PharmCal® CryoFlex™ 000302 (CryoFlex™ PPW)

2.3 Mil Gloss Topcoated White Polypropylene, Permanent Adhesive, 50 lb. Liner
FLX000302

Benefits

- Ideal for cryogenic specimen storage and testing applications: -112°F to 212°F (-80°C to 100°C) on PP vials; -320.8°F to 212°F (-196°C to 100°C) on aluminum panels/cassettes, EVA bags, and paper boxes
- Survives dry ice storage and transportation conditions
- 6-month change notification

Features

- 2.3 mil gloss topcoated white polypropylene
- Topcoat optimizes printability via narrow-format UV inkjet, flexographic, UV screen, UV letterpress, UV offset, and hot stamping
- High-performance permanent acrylic adhesive provides a good bond to low- and high-surface energy plastics, and glass for reliable performance in extreme cold temperatures
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting

Additional Details

Recommendations

Since laboratory storage/test conditions and procedures can vary significantly, be sure to thoroughly test the labels in the intended process/application environment. To achieve ultimate adhesion in cryogenic conditions, labels should be applied at room temperature.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.47	
Film	2.3 +/- 10%	58
Adhesive	0.6-0.7 +/- 0.1	15-18 +/- 3
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® PharmCal® CryoFlex™ 000302 (CryoFlex™ PPW)

2.3 Mil Gloss Topcoated White Polypropylene, Permanent Adhesive, 50 lb. Liner
FLX000302

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	50	550
Glass	45	495
HDPE	8	88
Polyester	40	440
Polypropylene	6	66

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	25	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	760	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-320.8°F to 212°F (-196°C to 100°C) on EVA Bags and paper boxes	
Minimum Application Temperature	35°F (2°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.