

# DPM® FWSRTS 4 Mil Flexible White Vinyl Hi Performance Adhesive for Rough/ Textured Surfaces Sheet Liner

Durable Goods and Equipment Labeling Flexible White Vinyl - Sheet Form - For Rough Textured Surfaces FLX000309

### **Benefits**

- UL-recognized under UL 969 UL File No. PGGU2.MH10170 Marking and Labeling System Materials Component
- cUL-recognized under UL File No. PGGU8.MH10170 Marking and Labeling System Materials Certified for Canada Component
- CSA accepted under CSA File No. 99214

### **Features**

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Compatible with most conventional and UV ink systems (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate
  and fiberglass
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting

## **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	12.2	
Film	3.5 +/- 10%	89
Adhesive	1.9-2.1 +/- 0.1	48-53 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# DPM® FWSRTS 4 Mil Flexible White Vinyl Hi Performance Adhesive for Rough/ Textured Surfaces Sheet Liner

Durable Goods and Equipment Labeling Flexible White Vinyl - Sheet Form - For Rough Textured Surfaces FLX000309

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	94	1034
Acrylic	130	1430
Glass	112	1232
Polypropylene	60	660

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	20	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	900	ASTM D 2979
Expected Exterior Life	Five years based on 2000 hours Xenon Arc exposure	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.