

# DPM® PWRTS 2 Mil Printable White PET High Performance Adhesive for Rough Textured Surfaces Roll Liner

Durable Goods and Equipment Labeling White Polyester for Rough Textured Surfaces - Roll Form FLX000315

### **Benefits**

- UL recognized under UL 969 UL File No. PGGU2.MH10170 Marking and Labeling System Materials Component
- cUL recognized under UL File No. PGGU8.MH10170 Marking and Labeling System Materials Certified for Canada Component
- CSA accepted under CSA File No. 99214

### **Features**

- 2.0 mil white polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Topcoated surface is compatible with most conventional and UV ink systems (we recommend evaluating the intended ink system for compatibility with the product under the application conditions)
- Acrylic adhesive offers high initial tack, high shear, and high ultimate bond to a wide variety of rough textured surfaces, including low-surface energy plastics and painted metal
- 50 lb. bleached kraft release liner offers good diecutability
- Ideal for roll to roll converting

#### **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	7.63	
Film	2.0 +/- 10 %	51
Adhesive	1.9-2.1 +/- 0.1	48-53 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# DPM® PWRTS 2 Mil Printable White PET High Performance Adhesive for Rough Textured Surfaces Roll Liner

Durable Goods and Equipment Labeling White Polyester for Rough Textured Surfaces - Roll Form FI X000315

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	87	957
Acrylic	122	1342
Glass	107	1177
Polypropylene	36	396

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	75	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	1650	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.