



# DPM® SS Silver Polyester High Performance Adhesive Sheet Liner

MM 200 Silver PTP L-344 90 PFW

FLX000322

## Benefits

- CSA Acceptance, L- Adhesives, UL Recognized

## Features

- 2 mil silver polyester
- Permanent acrylic adhesive offers high shear and excellent adhesion to metals, and high-surface energy plastics
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates

## Additional Details

## Technical Data

### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.11	
Film	2.0 +/- 10 %	51
Adhesive	0.9-1.0 +/- 0.1	23-25 +/- 3
Liner	6.9 +/- 10 %	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Acrylic	77	847
Glass	68	748
Polypropylene	15	165

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	30	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	1030	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.