



Benefits

- CSA Acceptance, L- Adhesives, UL Recognized

Features

- 2 mil silver polyester
- Permanent acrylic adhesive offers high shear and excellent adhesion to metals, and high-surface energy plastics
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 10.11 | |
| Film | 2.0 +/- 10 % | 51 |
| Adhesive | 0.9-1.0 +/- 0.1 | 23-25 +/- 3 |
| Liner | 6.9 +/- 10 % | 175 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 55 | 605 |
| Acrylic | 77 | 847 |
| Glass | 68 | 748 |
| Polypropylene | 15 | 165 |

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|--|
| Expected Shear (hours) | 30 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 1030 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | | |
| Service Temperature | -40°F to 302°F (-40°C to 150°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.