

# Flexcon® DrumCal™ 41028

 $3.1\,\mbox{Mil}$  White Vinyl, Permanent Adhesive, Sheet-Form Liner - BS 5609 Compliant FLX000332

## **Benefits**

2 year outdoor durability BS 5609 Section 2 compliant (salt water immersion)

#### **Features**

 $3.1 \, \mathrm{mil}$  flexible white vinyl provides excellent chemical resistance for drum labeling applications

The internal strength of the film facilitates removal during reconditioning

Excellent printability via most conventional ink systems (for laser printing, a press applied varnish is recommended)

Adhesive system is designed to bond well to painted steel, fiber and plastic drums

Product can be applied at low temperatures

Permanent pressure-sensitive adhesive possesses good adhesion properties, tack and chemical resistance

92 lb. sheet liner offers excellent layflat and feeding for efficient converting, imaging, and application handling

#### **Additional Details**

## **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Film	3.1 +/- 10 %	79
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	7.4 +/- 10 %	188

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® DrumCal™ 41028

 $3.1\,\mbox{Mil}$  White Vinyl, Permanent Adhesive, Sheet-Form Liner - BS 5609 Compliant FLX000332

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	85	935
Acrylic	102	1122
Glass	94	1034
Polypropylene	61	671

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	15	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	750	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.