

# Flexcon® FlexMark® V 400 IFW V-478 90 PFW

Consumer Durables Flexible White Vinyl FLX003787

## **Benefits**

Ideal for sheet-form converting

## **Features**

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Compatible with most conventional and UV ink systems (we recommend evaluating the intended ribbon and ink system for compatibility with the product under the application conditions)
- V-478 is ideal for use in harsh environments, including areas that have varying temperatures
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting

#### **Additional Details**

End Use Applications: Compliance Labels, Warning & Instructional Labels, Nameplates, Brand Identity Labels

## **Technical Data**

#### **Physical Properties**

| Thickness (Mils [microns]) | Mils            | Microns |
|----------------------------|-----------------|---------|
| Total Product              | 11.25           |         |
| Film                       | 3.5 +/- 10 %    | 89      |
| Adhesive                   | 1.0-1.1 +/- 0.1 | 25-28   |
| Liner                      | 6.9 +/- 10 %    | 175     |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® FlexMark® V 400 IFW V-478 90 PFW

Consumer Durables Flexible White Vinyl FLX003787

#### **Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel    | 102           | 1122  |
| Acrylic            | 111           | 1221  |
| Glass              | 107           | 1077  |
| Polypropylene      | 100           | 1100  |

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

| Additional Properties           | Value   | Test Method  |
|---------------------------------|---|--|
| Expected Shear (hours)          | 5   | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g)                        | 950   | ASTM D 2979  |
| Expected Exterior Life          | Two years   |  |
| Additional Information          |   |  |
| Service Temperature             | -40°F to 176°F (-40°C to 80°C)                            |  |
| Minimum Application Temperature | 32°F (0°C)  |  |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% relative humidity |  |

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.