

# FlexMark® V 400 Frosty Clear TC-106 L-29 Spec 50K-8

Consumer Durables Gloss Topcoated Frosty Clear Vinyl FLX000409

## **Benefits**

• UL recognized under UL 969 - UL File No.PGGU2.MH10170 Marking and Labeling System Materials - Component

## **Features**

- 3.5 mil frosty clear vinyl with good chemical resistance to mild cleaning products that's easy to apply
- Printable via water flexo (please test for ink adhesion with your specific ink chemistry)
- Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces
- Permanent clear overlaminating pressure-sensitive acrylic adhesive offers excellent clarity and performance
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting

### **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	7.9	
Film	3.5 +/- 10 %	89
Adhesive	0.8-0.9 +/- 0.1	20-23 +/-3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



## FlexMark® V 400 Frosty Clear TC-106 L-29 Spec 50K-8

Consumer Durables Gloss Topcoated Frosty Clear Vinyl FLX000409

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	47	517
Acrylic	60	660
Glass	54	594
Polypropylene	14	154

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	15	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	500	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information	72 hr water immersion + 24 hr recovery vs 72 RT on SS panel (24 hr dwell time on SS panel before immersion) No visual change or adhesio loss	
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Six months stored at 70°F (21°C) and 50% rela humidity	tive

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.