

# Flexcon® FlexMark® V 400 F White TC-106 L-156 Spec 50K/Q-8

Industrial Labeling Product Topcoated White Vinyl FLX004325

### **Benefits**

- Excellent chemical resistance for drum labeling applications
- UL recognized under UL 969 UL File No. PGGU2.MH10170 Printing Materials Component

#### **Features**

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Printable via water flexo (please test for ink adhesion with your specific ink chemistry)
- High-performance, aggressive permanent acrylic adhesive provides a permanent bond to a wide range of surfaces, including powder coated paint and metal
- Backed with a 50 lb. semi-bleached kraft release liner that is Quilon®\* coated to prevent label pick-off

### **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	8.3	
Film	3.5 +/- 10 %	89
Adhesive	1.3-1.4 +/- 0.1	33-36 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® FlexMark® V 400 F White TC-106 L-156 Spec 50K/Q-8

Industrial Labeling Product Topcoated White Vinyl FLX004325

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	128	1408
Acrylic	117	1287
Glass	121	1331
Polypropylene	35	385

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	1	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	810	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.