



### Benefits

- UL recognized under UL 969 – UL File No. PGJ12.MH16635 Printing Materials – Component

### Features

- 2.0 mil destructible white polyethylene destructs or distorts easily
- Topcoat optimizes ink receptivity for UV, solvent, and water flexo; UV and solvent screen; UV letterpress; UV offset; hot stamping; and thermal transfer
- Aggressive permanent rubber based adhesive offers excellent adhesion to a wide variety of surfaces
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting

### Additional Details

### Technical Data

#### Physical Properties

| Thickness (Mils [microns]) | Mils            | Microns     |
|----------------------------|-----------------|-------------|
| Total Product              | 6.6             |             |
| Film                       | 2.0 +/- 10 %    | 51          |
| Adhesive                   | 1.0-1.1 +/- 0.1 | 25-28 +/- 3 |
| Liner                      | 3.1 +/- 10 %    | 79          |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m)                      |
|--------------------|---------------|----------------------------|
| Stainless Steel    |               | Film fractures during test |
| Acrylic            |               | Film fractures during test |
| Glass              |               | Film fractures during test |
| Polypropylene      |               | Film fractures during test |

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

| Additional Properties           | Value   | Test Method  |
|---------------------------------|---|--|
| Expected Shear (hours)          | 5 + Film rips during test                                 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g)                        | 630   | ASTM D 2979  |
| Expected Exterior Life          | Indoor use only   |  |
| Additional Information          |   |  |
| Service Temperature             | -40°F to 200°F (-40°C to 93°C)                            |  |
| Minimum Application Temperature | 50°F (10°C)   |  |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% relative humidity |  |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.