

Benefits

- UL recognized under UL 969 - UL File No. PGJl2.MH16635 Printing Materials - Component
- CSA accepted with specific thermal transfer ribbon(s) and printer(s) under CSA standard C22.2 No. 0.15-95
- CSA accepted under CSA File No. 99214
- Order custom widths without purchasing a whole master through Flexcon® FlexChoice™ for Durables

Features

- 1.0 mil clear polyester film provides excellent clarity and label protection
- Topcoat resists smudging and abrasion when printed with resin and wax/resin thermal transfer ribbons
- Overlaminating polyester resists temperature extremes, abrasion and chemical exposure for maximum label protection
- Adhesive exhibits good clarity and cold-flow properties, resulting in good wet-out performance
- 44 lb. polycoated natural Kraft release liner ideal for roll-form converting
- Liner provides a good diecutting base and allows for high-speed dispensing

Additional Details

Please note: Not recommended for fan-fold applications

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	1.0 +/- 10%	25
Adhesive	0.8-0.9 +/- 0.1	20-23 +/- 3
Liner	3.0 +/- 10%	76

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	34	374
Acrylic	45	495
Glass	29	319
Polypropylene	5	55

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear	25	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack	320	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.