



# Flexcon® SwitchMark® 022 2 MIL Polyester with Adhesive One Side On A 90 PFW Liner

Membrane Switch - Overlamine 0-2-2 (.004" Total Thickness)  
FLX000478

## Benefits

- RoHS 2002/95/EC Compliant; RoHS 2003/11/EC Compliant, RoHS 76/69/EEC Compliant, UL Recognized

## Features

Flexcon® SwitchMark® spacer components, overlaminates and laminating adhesives are specifically engineered for demanding membrane switch applications. Specially formulated pressure-sensitive adhesives are designed to bond well to a variety of surfaces. The adhesive also allows the necessary rework time to minimize waste in assembly from misaligned components.

- Excellent high-temperature, humidity and chemical resistance which allows the switch to remain functional in extreme environments
- Film is dimensionally stable during the conventional printing process
- Adhesive is compatible with a wide range of solvent and UV ink systems, including conductive, decorative and dielectric inks
- High-performance permanent pressure-sensitive acrylic adhesive bonds well to high-surface energy plastics, metal and paint\*
- Superior mechanical properties ensure long-term membrane switch performance without delamination (ASTM F 1578-00)
- Product can be repositioned within the first few minutes of application allowing easy correction of assembly mistakes
- Adhesive is compatible with a wide range of solvent and UV ink systems, including conductive, decorative and dielectric inks
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting
- Product is ideal for dome retention, tail insulating, tail reinforcing and printing conductive circuit layers
- Product is available in rolls and sheets

## Additional Details

\*Recommendations: Application surfaces must be above 50°F (10°C). Surfaces must be clean and dry to obtain best adhesion results. Firm and even laminating pressure helps promote adhesive contact and improves bond strength. Always laminate to exclude air entrapment.

## Technical Data

### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Film	2.0 +/- 10%	51
Adhesive	1.9-2.1 +/- 0.2 (5)	48-53
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® SwitchMark® 022 2 MIL Polyester with Adhesive One Side On A 90 PFW Liner

Membrane Switch - Overlamine 0-2-2 (.004" Total Thickness)  
FLX000478

## Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Conductive Solvent Screen Ink	56	616
Dielectric UV Screen Ink - Ach	64	704
Polycarbonate	73	803
Polyester	82	902

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear		
Tack	260	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.