



# Flexcon® SwitchMark® 272 7 MIL POLYESTER W/ADHESIVE BOTH SIDES ON 90 PFW ONE SIDE/80BPFM PRINTED ONE SIDE

Membrane Switch - Component Spacer - 2-10-2 (.014" Total Thickness)  
FLX000486

## Benefits

- RoHS 2002/95/EC Compliant
- RoHS 2003/11/EC Compliant, RoHS 76/69/EEC Compliant, UL Recognized"
- Superior mechanical properties ensure long-term membrane switch performance without delamination (ASTM F 1578-00)
- Adhesive system has UL recognition under UL746C, Polymeric Adhesive Systems, Electrical Equipment - Component and UL969, Marking & Labeling Systems Materials Component 302°F (150°C)

## Features

- Flexcon® SwitchMark® spacer components, overlaminates and laminating adhesives are specifically engineered for demanding membrane switch applications. Specially formulated pressure-sensitive adhesives are designed to bond well to a variety of surfaces. The adhesive also allows the necessary rework time to
- 7.0 mil clear polyester film
- Adhesive is compatible with a wide range of solvent and UV ink systems, including conductive, decorative and dielectric inks
- High-performance permanent pressure-sensitive acrylic adhesive bonds well to high-surface energy plastics, metal and paint\*
- Product can be repositioned within the first few minutes of application allowing easy correction of assembly mistakes
- Adhesive is compatible with a wide range of solvent and UV ink systems, including conductive, decorative and dielectric inks
- Backed with an 80 lb. two-sided semi-bleached polycoated mando release liner, backside printed with a black stripe

## Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	22.6	
Film	7.0 +/- 10%	178
Adhesive	1.9-2.1 +/- 0.1 (3)	48-53
Adhesive 2	1.9-2.1 +/- 0.1 (3)	48-53
Liner	6.9 +/- 10%	175
Liner 2	4.8 +/- 10%	122

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® SwitchMark® 272 7 MIL POLYESTER W/ADHESIVE BOTH SIDES ON 90 PFW ONE SIDE/80BPFM PRINTED ONE SIDE

Membrane Switch - Component Spacer - 2-10-2 (.014" Total Thickness)

FLX000486

## Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
ABS	26	286
Alkyd Enamel Paint	35	385
Conductive Solvent Screen Ink	26	286
Decorative Solvent Screen Ink	34	374
Decorative UV Screen Ink - Coa	76	836

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	220	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information	Dielectric Strength (minus adhesive) 11.0 KV/mil (DC)	
Service Temperature	-40°F to 302°F (-40°C to 150°C) with polyester film	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.