



FlexMount® TT 200 L-344 60 LA PFW

2 Mil Permanent Adhesive Transfer Tape 60 lb liner
FLX000487

Benefits

- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

Features

- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- Backed with a 60 lb. bleached white kraft liner, polycoated and release coated on two sides
- Release liner has excellent moisture stability and is a good base for rotary, flatbed and steel rule diecutting

Additional Details

Learn more about [Flexcon's adhesive transfer tapes](#)

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 6.55 | |
| Adhesive | 1.9-2.1 +/- 0.1 | 48-53 +/- 3 |
| Liner | 4.3 +/- 10 % | 109 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
|--------------------|---------------|-------|

Test Method:

| Additional Properties | Value | Test Method |
|---------------------------------|---|--|
| Expected Shear (hours) | 25 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 950 | ASTM D 2979 |
| Expected Exterior Life | Dependant on life of substrate - suitable for outdoor use | |
| Additional Information | | |
| Service Temperature | -40°F to 302°F (-40°C to 150°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.