



Benefits

- Ideal for sheet-form converting

Features

- 3.25 mil flexible white vinyl film provides durability and easy installation
- Removable pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including chrome-coated metal, chrome-coated plastic, glass, auto glass and painted plastic
- Backed with a layflat, sheet-form backside printable release liner for bumper sticker applications that require a coupon or promotional advertisement

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|---------------------|---------|
| Total Product | 11.25 | |
| Film | 3.1 +/- 10 % | 79 |
| Adhesive | 0.7-0.8 +/- 0.1 (3) | 18-20 |
| Liner | 7.4 +/- 10 % | 188 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 33 | 363 |
| Acrylic | 46 | 506 |
| Glass | 30 | 330 |
| Polypropylene | 24 | 264 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear (hours) | 2 | ASTM 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 350 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | Not to be used for setting specifications. Due to the custom nature of this product, the data presented are based on three or less production runs. | |
| Service Temperature | -40°F to 176°F (-40°C to 80°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% RH | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.