

Benefits

Features

- 5.0 mil gloss topcoated bright brushed silver polyester film offers good durability
- Topcoat resists smudging and abrasion when printed with resin and wax/resin thermal transfer ribbons
- Permanent acrylic adhesive offers medium tack, high shear and excellent adhesion to a variety of metal and plastic surfaces, including polypropylene, polyethylene, PORON® and Kushon® cellular rubber products
- Backed with a 50lb. semi-bleached kraft release liner that is Quilon®* coated to prevent label pickoff†

Additional Details

*PORON® is a registered trademark of Rogers Corporation. Kushon® is a registered trademark of Griswold Products, LLC.
†Quilon® is a registered trademark of Zaclon LLC.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|------|---------|
| Total Product | 10.5 | |

Test Method:

Adhesion Properties

| | | |
|--------------------|---------------|-------|
| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|

Test Method:

| Additional Properties | Value | Test Method |
|---------------------------------|-------|-------------|
| Expected Shear (hours) | | |
| Tack (g) | | |
| Expected Exterior Life | | |
| Additional Information | | |
| Service Temperature | | |
| Minimum Application Temperature | | |
| Storage Stability | | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.