

Benefits

- Permanent pressure-sensitive acrylic adhesive bonds well to glass and high-surface energy plastics

Features

- 1.0 mil double-faced clear polyester film mounting film coated with a permanent pressure-sensitive acrylic adhesive on one side and a removable pressure-sensitive adhesive on the other side
- Adhesive bonds well to printed base film surfaces
- Backed with an ultra smooth clear polyester release liner

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.66	
Film	1.0 +/- 10%	25
Adhesive	1.0-1.1 +/- 0.1 (3)	25-28
Adhesive 2	1.0-1.1 +/- 0.1 (3)	25-28
Liner	1.0 +/- 5%	25
Liner 2	1.0 +/- 5%	25

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
ABS	50	550
Acrylic	45	495
Painted Metal	26	286
Polypropylene	11	121
Stainless Steel	30	330

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	150	ASTM D 2979
Expected Exterior Life	Dependant on life of substrate - suitable for outdoor use	
Additional Information		
Service Temperature	-20°F to 302°F (-29°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.