

Flexcon® ThinFlex™ PP 160 H White TC-458 V-344 TracRite™ 120

Primary and Secondary Labeling White Polypropylene FLX052583

Benefits

- High-performance, aggressive permanent acrylic adhesive with excellent wet-out characteristics
- Backed with Flexcon® TracRite™ 120 polyester release liner for excellent on-press performance for tight registration graphics

Features

- Topcoated 1.6 mil hard white polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity and product contents
- Film opacity is ideal for achieving high impact graphics, and the no label look on white containers
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, narrow-format UV inkjet, roll-form dry toner, UV rotary screen, UV letterpress and hot stamping
- V-344 adhesive adheres to a wide range of container types including low-surface HDPE, and printed graphics

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	3.95	
Film	1.6 +/- 10 %	41
Adhesive	0.7-0.8 +/- 0.1	18-20 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® ThinFlex™ PP 160 H White TC-458 V-344 TracRite™ 120

Primary and Secondary Labeling White Polypropylene FLX052583

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	40+	440+
Glass	40+	440+
Polypropylene	29	319
Acrylic	40+	440+

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	40	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	800	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.