



Flexcon® ThermlFilm® NexGen™ 25120

2.0 Mil Gloss Topcoated Bright Brushed Silver Polyester, Permanent Adhesive, Roll-Form Liner
FLX054112

Benefits

- 50 lb. bleached kraft release liner made from up to 30% post-consumer waste, ideal for roll form converting
- Liner is suitable for optical sensing on most thermal transfer printers
- UL recognized under UL 969 - UL File No. PGJ12.MH16635 Printing Materials - Component
- cUL recognized under UL File No. PGJ18.MH16635 - Printing Materials Certified for Canada - Component - under CAN/CSA standard C22.2, No. 0.15
- CSA accepted under CSA File No. 99214

Features

- 2.0 mil gloss topcoated silver polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Bright brushed silver polyester provides a high-end appearance
- Topcoat is more universally printable than other thermal transfer printable products
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- 50 lb. bleached kraft release liner made from up to 30% post-consumer waste, ideal for roll form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.45	
Film	2.0 +/- 10%	51
Adhesive	0.8-0.9 +/- 0.1 (3)	20-23
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® ThermoFilm® NexGen™ 25120

2.0 Mil Gloss Topcoated Bright Brushed Silver Polyester, Permanent Adhesive, Roll-Form Liner
FLX054112

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	77	847
Glass	68	748
Stainless Steel	55	605
Polypropylene	15	165
Acrylic Powder Paint	58	638

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	1030	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.