

### Benefits

- Tight weave of fabric allows for crisp, sharp color when printed via solvent and UV inkjet, UV and conventional offset, and UV and solvent screen
- CONEG and CPSIA compliant

### Features

- 6.0 mil light weight, polycoated white fabric film with a unique woven texture
- Tight weave of fabric allows for crisp, sharp color when printed via solvent and UV inkjet, UV and conventional offset, and UV and solvent screen
- High-performance permanent adhesive designed to adhere well to flat, smooth painted (non-vinyl) wall boards
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting

### Additional Details

Please click [here](#) to view [Flexcon's Wall Graphics Technical Guide and Application Instructions](#).

For Inkjet Printing:

- Typical max. ink limit = 250%
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

### Technical Data

#### Physical Properties

| Thickness (Mils [microns]) | Mils                | Microns |
|----------------------------|---------------------|---------|
| Total Product              | 15.45               |         |
| Film                       | 6.0 +/- 10%         | 152     |
| Adhesive                   | 1.4-1.5 +/- 0.1 (3) | 36-38   |
| Liner                      | 6.9 +/- 10%         | 175     |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

| Ultimate Peel from             | Average Oz/In | (N/m) |
|--------------------------------|---------------|-------|
| Smooth Painted (non vinyl) Wal | 23            | 253   |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties           | Value                                      | Test Method |
|---------------------------------|--|-------------|
| Expected Shear (hours)          |  |             |
| Tack (g)                        | 900  | ASTM D 2979 |
| Expected Exterior Life          | Indoor use only                            |             |
| Additional Information          |  |             |
| Service Temperature             | -40°F to 176°F (-40°C to 80°C)             |             |
| Minimum Application Temperature | 50°F (10°C)                                |             |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% RH |             |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.