



ReflectaMark® PM 400 White Reflective V-344 90 PFW

Safety / Visibility Applications White Polyester Retroreflective - Sheet Form
FLX055420

Benefits

- Backed with a 90 lb. two-side polycoated layflat release liner ideal for sheet-form converting

Features

- 2 mil white polyester film with 2 mil glass bead reflective coating offers higher reflectivity and reflects from a longer distance than standard promotional grade film
- Printable via TTR, flexo and screen. Can be topcoated for additional print technologies (Including Digital and Conventional)
- Permanent pressure-sensitive acrylic adhesive bonds well to low- and high-surface energy plastics, metal, powder coated paint, paint, ceramic, paper/fiber, glass and fiberglass

Additional Details

For reflectivity data, [click here](#).

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 12.1 | |
| Film | 4.0 +/- 15% | 102 |
| Adhesive | 1.0-1.1 +/- 0.1 | 25-28 +/- 3 |
| Liner | 6.9 +/- 10% | 175 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|--------------------------------|
| Acrylic | | Film destructs during adhesion |
| Glass | | Film destructs during adhesion |
| Polypropylene | 15 | 165 |
| Stainless Steel | | Film destructs during adhesion |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|--|
| Expected Shear (hours) | 25 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 660 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | | |
| Service Temperature | -40°F to 176°F (-40°C to 80°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.