

### Flexcon® DPM® LSE™ MM 200 Silver Matte TC-716 L-778 94 PFW

Durable Goods and Equipment Labeling for Low-Energy Surfaces Silver Matte Polyester - Sheet Form FLX055428

#### **Benefits**

- No surface preparation required before application. UL-recognized and certified with inks from four leading manufacturers
- CSA accepted under CSA File No. 99214
- UL-recognized and certified with inks from four leading manufacturers
- Topcoat is more universally printable than other thermal transfer printable products
- Permanently bonds to a variety of low surface energy plastics, painted metal, powder coated paint, polycarbonate, and fiberglass
- Adhesive eliminates the need to prime or flame treat the surface of TPO plastics

#### **Features**

- CUL Recognized, L- Adhesives, UL Recognized
- 2.0 mil gloss topcoated silver matte polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- · High-performance modified acrylic pressure-sensitive adhesive is the most aggressive adhesive for low surface energy plastics

### **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	10.25	
Film	2.0 +/- 10%	51
Adhesive	0.9-1.0 +/- 0.1 (3)	23-25
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)



## Flexcon® DPM® LSE™ MM 200 Silver Matte TC-716 L-778 94 PFW

 ${\bf Durable\ Goods\ and\ Equipment\ Labeling\ for\ Low-Energy\ Surfaces\ Silver\ Matte\ Polyester\ -\ Sheet\ Form\ FLX055428}$ 

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic Powder Paint	72	792
Stainless Steel	72	792
Epoxy KF4	61	671
Polypropylene	46	506
Epoxy Powder Paint	62	682

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	730	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

# **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.