



## Flexcon® FlexMount® TT 400 L-606 84 LA PFT

4 Mil Permanent Adhesive Transfer Tape on a Single 84lb layflat differential release Liner  
FLX000564

### Benefits

- Adhesive exhibits exceptional performance on textured and uneven surfaces

### Features

- 4.0 mil transfer adhesive
- Permanent acrylic adhesive offers medium tack, high shear and excellent adhesion to a variety of metal and plastic surfaces, including polypropylene, polyethylene, PORON® and Kushon® cellular rubber products
- Adhesive offers high initial tack, high shear, and high ultimate bond to a wide variety of rough textured surfaces, including low-surface energy plastics and painted metal
- Backed with an 84 lb. natural kraft polycoated layflat differential release liner ideal for roll-to-sheet converting
- Heavy release liner has excellent moisture stability and is a good base for flatbed and steel rule diecutting

### Additional Details

#### Technical Data

##### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.2	
Adhesive	3.9-4.1 +/- 0.2 (5)	99-104
Liner	6.4 +/- 10%	163

Test Method: ASTM D 3652 (Modified for use with non-tape product)



# Flexcon® FlexMount® TT 400 L-606 84 LA PFT

4 Mil Permanent Adhesive Transfer Tape on a Single 84lb layflat differential release Liner  
FLX000564

## Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
--------------------	---------------	-------

Test Method:

Additional Properties	Value	Test Method
Expected Shear (hours)	40	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	1710	ASTM D 2979
Expected Exterior Life	Depends on substrates, adhesive is suitable for outdoor use	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.