



### Benefits

- Adhesive complies with FDA 175.105 for indirect food contact

### Features

- 2 mil flexible clear topcoated BOPP film is suitable for irregular shaped surfaces or large panel surfaces, including full squeeze and crimp
- Topcoat is compatible with a wide range of inks including UV Flexo, UV Screen, UV Letterpress, Water Flexo, Solvent Flexo and Screen
- High-performance, permanent acrylic adhesive adheres to a wide range of container types including low-surface energy HDPE
- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing

### Additional Details

#### Technical Data

##### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.2	
Film	2.0 +/- 10%	51
Adhesive	0.5-0.6 +/- 0.1 (3)	13-15
Liner	1.2 +/- 10%	30

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	42	462
Glass	38	418
Stainless Steel	41	451
Polypropylene	20	220
Aluminum	50	550

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear		
Tack	660	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.