



Flexcon® Shelf Select® FWFZR WHITE VINYL REMOVABLE ADHESIVE SHEET LINER

Shelf Marking - Shelf Tags, White Vinyl Removable Adhesive Sheet Liner
FLX056661

Benefits

- 92 lb. liner ensures a lay flat product through the printer, converting, and application at the shelf including the refrigerator and the freezer

Features

- 3.0 mil flexible white vinyl film printable via flexographic and laser (with press applied varnish) with good chemical resistance to mild cleaning products
- Removable adhesive bonds well to powder-coated paint, metal, high- and low-surface energy plastics, and glass
- Clean removability allows for quick and efficient price or promotion changes
- White, layflat two-side polycoated release liner with a highly engineered backside, friction-coated layer which enables excellent tracking on press and reliable feeding through tabletop and big box laser printers

Additional Details

FLEXcon recommends that the product be applied to a clean, dry surface for optimum results. FLEXcon also recommends "fit-for-use" testing under actual conditions.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 10.45 | |
| Film | 3.0 +/- 10% | 76 |
| Adhesive | 0.6-0.7 +/- 0.1 | 15-18 +/- 3 |
| Liner | 6.7 +/- 10% | 170 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Acrylic | 26 | 286 |
| Polypropylene | 21 | 231 |
| Stainless Steel | 37 | 407 |
| Styrene | 35 | 385 |
| Painted Metal | 25 | 275 |

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|--|-------------|
| Expected Shear (hours) | | |
| Tack (g) | 230 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -20°F to 176°F (-29°C to 80°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | One year stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.