

Flexcon® OptiFlex® MPP20413 2.0 Mil Silver Polypropylene, TC, V-01 ADH, 1.2 Mil Polyester Liner

Primary and Secondary Labeling Silver Polypropylene FLX056721

Benefits

- Excellent surface smoothness allows for optimum ink laydown
- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Adhesive complies with FDA 175.105 for indirect food contact
- Product has been 3rd party tested for Higher Pressure Processing (HPP) and adhesive was found to have the necessary strength and compatibility to withstand the HPP conditions
- Order custom widths without purchasing a whole master through Flexcon® FlexChoice™ for Packaging

Features

- Topcoated 2.0 mil hard silver polypropylene (BOPP) offers resistance to shrinkage, moisture, and humidity
- Excellent surface smoothness allows for optimum ink laydown
- Printable via UV, solvent & water flexo, UV inkjet (Xeikon Jetrion 4000 series and Domino), UV screen, UV letterpress, and hot stamping
- High-performance, permanent acrylic adhesive adheres to a wide range of container types including low-surface energy HDPE
- Polyester release liner for excellent on-press performance for tight-registration graphics & contains up to 60% post industrial recycled content

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 4 | |
| Film | 2.0 +/10% | 51 |
| Adhesive | 0.5-0.6 +/- 0.1 | 13-15 +/- 3 |
| Liner | 1.2 +/- 5% | 30 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® OptiFlex® MPP20413 2.0 Mil Silver Polypropylene, TC, V-01 ADH, 1.2 Mil Polyester Liner

Primary and Secondary Labeling Silver Polypropylene FLX056721

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 54 | 594 |
| Acrylic | 54 | 594 |
| Glass | 40 | 440 |
| Polypropylene | 23 | 253 |
| Styrene | 41 | 451 |

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear (hours) | 10 | ASTM 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 790 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -40°F to 212°F (-40°C to 100°C) | |
| Minimum Application Temperature | 35°F (1.7°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.