

Flexcon® DrumCal™ 51932

 $2.3\ Mil\ Top coated\ White\ Polypropylene,\ Permanent\ Adhesive,\ Roll-Form\ Liner\ -\ BS\ 5609\ Compliant\ FLX056886$

Benefits

- BS 5609 Section 2 compliant (salt water immersion)
- BS 5609 Section 3 compliant with a variety of thermal transfer ribbons

Features

- 2.3 mil BBP free white polypropylene film
- Topcoated surface optimizes printability with thermal transfer resin, UV inkjet, flexographic, rotary screen, rotary letterpress and hot stamping
- General purpose permanent adhesive bonds well to painted steel, fiber and plastic drums
- Backed with a 50 lb. bleached kraft release liner made from up to 30% post-consumer waste, ideal for roll form converting
- Liner is remoisturized for better stability and layflat

Additional Details

Pertaining to BBP Free: None of the RoHS, RoHS 2015, REACH, CPSIA and California Prop 65 substances are knowingly used or intentionally added during the manufacturing process.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.65	
Film	2.3 +/- 10%	58
Adhesive	0.8-0.9 +/- 0.1 (3)	20-23
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® DrumCal™ 51932

 $2.3 \ Mil \ Top coated \ White \ Polypropylene, \ Permanent \ Adhesive, \ Roll-Form \ Liner - \ BS \ 5609 \ Compliant \ FLX056886$

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	49	539
Stainless Steel	39	429
ABS	64	704
Polypropylene	18	198
Aluminum	63	693

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	650	ASTM D 2979
Expected Exterior Life	One year	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.